



UNIVERSITI PUTRA MALAYSIA

**SYNTHESIS AND CHARACTERIZATION OF NOVEL
PLASMID-LAYERED DOUBLE HYDROXIDES
NANOBIOHYBRIDS FOR GENE DELIVERY**

MAS JAFFRI MASARUDIN

FBSB 2008 14

Dedicated to arwah Atuk Yusof, and arwah Wan Zaharah.

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in
fulfilment of the requirement for the degree of Master of Science

**SYNTHESIS AND CHARACTERIZATION OF NOVEL PLASMID-LAYERED
DOUBLE HYDROXIDES NANOBIOHYBRIDS FOR GENE DELIVERY**

By

MAS JAFFRI MASARUDIN

October 2008

Chairperson: Professor Datin Khatijah Mohd. Yusoff, PhD

Faculty : Biotechnology and Biomolecular Sciences

One of the hindering problems faced by conventional gene delivery systems into cells is their efficiency in its delivery and integration. DNA and other genetic materials are easily degraded in both the extracellular as well as intracellular matrix by both endonuclease activities and physiological conditions of the cellular environment. Therefore, research insights have focused on utilizing the emerging field of nanotechnology to overcome this problem. For this reason, a layered nanomaterial, Mg/Al-LDH based on the layered double hydroxide (LDH) system was synthesized at pH 10.0 at different Mg to Al ratios, to determine whether it can be used as a vector for gene delivery. A plasmid DNA, encoding the green fluorescent protein reporter gene, was intercalated into the LDH intergallery region; previously occupied by nitrate anions. Successful occupation of the

circular DNA was confirmed by expansions within the intergallery spacing of the LDH from powder x-ray diffraction analysis. Fourier-transform infrared spectroscopy further revealed the presence of exclusive functional groups belonging to both DNA and LDH in the nanobiohybrid product, and by both CHNS as well as gel electrophoresis data, the plasmid DNA was confirmed to be successfully intercalated within the LDH host. The effects of the host on cells were then evaluated using MTT assay on two cell lines, and the synthesized LDH hosts were found to have no significant lethal effects on cell viability. Microscopic studies using SEM and TEM later revealed the nanobiohybrid size to be within the nano-meter range, which was found to enhance its uptake by cells. Cells transfected with the nanobiohybrid showed successful expression of the GFP gene compared to controls, as observed using fluorescence microscopy. The nanobiohybrid was found to not only deliver the gene into cells, but gene expression efficiency using the host for transfection was even comparable to a commercially available, high cost transfection vector in the market. Compared to the commercial vector, the LDH host was also shown to provide sufficient protection of the intercalated plasmid from degradation by the DNase I and *XhoI/KpnI* restriction enzymes, showing the potential of using the LDH host as an alternative delivery vector for gene delivery.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

**SINTESIS DAN PENCIRIAN NANOBIOHIBRID PLASMID-LAPISAN
BERGANDA HIDROKSIA UNTUK PEMINDAHAN GEN**

Oleh

MAS JAFFRI MASARUDIN

Oktober 2008

Pengerusi : Professor Datin Khatijah Mohd. Yusoff, PhD

Fakulti : Bioteknologi dan Sains Biomolekul

Salah satu dari masalah yang sering dihadapi berkenaan proses transfeksi gen ke dalam sel adalah dalam pemindahan serta integrasinya ke dalam genom sel perumah. Ini kerana, DNA serta bahan genetik seumpamanya amat mudah mengalami degradasi di persekitaran dalam dan luar sel; melalui tindakan enzim-enzim *endonuclease*, di samping keadaan fisiologi sel terbabit. Oleh itu, untuk menangani masalah ini, penyelidikan dalam terapi gen telah melibatkan penggunaan sains nanoteknologi, yang umumnya semakin mendapat perhatian. Di dalam penyelidikan ini, sejenis bahan nano yang berasaskan kepada sebatian lapisan berganda hidroksida (LDH), Mg/Al-LDH telah disintesis pada pH 10 dalam komposisi Mg dan Al yang berbeza, bagi menilai keupayaan bahan nano ini untuk dibangunkan sebagai suatu vektor alternatif bagi transfeksi gen. Satu plasmid DNA, mengandungi gen bagi ekspresi protein floresen hijau dalam sel, telah diinterkalasikan di antara ruangan lapisan LDH tersebut. Dengan

menggunakan teknik pembelauan sinar x-ray, pembentukan sebatian nanohibrid baru yang mengandungi DNA plasmid diinterkalasikan ke dalam LDH telah ditentukan; melalui peningkatan saiz ruang antara lapisan LDH tersebut yang lebih besar. Daripada spektrum F-TIR yang diperolehi, sampel nanobiohibrid yang telah disintesis itu didapati mengandungi struktur kumpulan-kumpulan kimia yang dipunyai kedua-dua DNA plasmid dan LDH. Analisis kandungan menggunakan teknik CHNS serta elemen organik-tak organik, menunjukkan bahawa sampel nanobiohibrid tersebut mempunyai komponen DNA, dan seterusnya membuktikan bahawa interkalasi DNA plasmid telahpun berlaku. Analisis ketoksikan menggunakan asei MTT telah dijalankan bagi menentukan sama ada bahan nano LDH tersebut adalah toksik terhadap sel-sel yang ingin ditransfeksi. Asei tersebut mendapati bahawa bahan nano LDH yang digunakan adalah tidak toksik kepada sel. Analisis mikroskopi SEM dan TEM mendapati semua sampel LDH dan nanobiohybrid tersebut berbentuk heksagon serta wujud pada saiz nanometer. Ekspresi gen dalam sel dengan transfeksi menggunakan sampel nanohibrid yang telah disintesis mendapati bahawa bahan nano LDH tersebut mampu memindahkan gen GFP ke dalam sel. Menggunakan mikroskop floresen, kadar ekspresi gen positif menggunakan bahan nano tersebut adalah tinggi, dan setaraf berbanding transfeksi menggunakan suatu vektor transfeksi gen komersial, tetapi didapati pada harga yang lebih tinggi. Dengan menggunakan bahan nano tersebut sebagai vektor transfeksi, didapati bukan sahaja boleh memindahkan gen tersebut dengan baik ke dalam sel, tetapi juga berupaya melindungi DNA plasmid yang diselitkan daripada tindakan enzim

pembatas *XhoI/KpnI* serta enzim DNase I. Keupayaan bahan nano LDH ini dalam melindungi dan membantu meningkatkan pemindahan suatu gen ke dalam sel menunjukkan keupayaan dan potensi untuk digunakan serta dibangunkan sebagai suatu vektor transfeksi alternatif untuk teknologi pemindahan gen.

ACKNOWLEDGEMENTS

Alhamdulillah, praise Allah the Almighty for His blessings upon the completion of this novel study. From Him this knowledge resides and through Him it is shared.

My sincerest, utmost gratitude I owe my esteemed group of supervisors – Prof. Datin Paduka Dr. Khatijah Mohd Yusoff, Prof. Dr. Mohd Zobir Hussein and Prof. Dr. Raha Abdul Rahim. All their valuable insights, advice, guidance and encouragements were pivotal upon the compilation of this work. Thank you very much for your unconditional commitment and warm support throughout these few years. They are my greatest critics; and without them this section would cease to be penned down.

Special thanks to the staff of Institute of Advanced Technology UPM especially to Mrs. Sarinawani, Mrs. Rosnah, Mr. Kadri, Institute of Bioscience, and the Faculty of Biotechnology and Biomolecular Sciences for the technical guidance and usage of instruments. Thank you to the Faculty of Biotechnology and Biomolecular Sciences UPM for sponsoring my study leave and also the Ministry of Science, Technology and Innovation Malaysia (MOSTI) for funding this project (IRPA grant 01-02-003-BTK/ER-006).

To my colleagues whom I regard as my own family; my AMNL labmates Mokrish, Adila, Norhayati, Ikin, Faiza, Zahiri, Siti Halimah and Budy; it was a challenging road but thank you for making it bearable and worthwhile. My extended labmates



Rajik, Max, Sim, Kah Fai, Lai, Swee Tin, Eddie, Erin, Kie Hie, Michelle, Aeid and Pala. My close friends Fadil, Azfar, Zaid and Faylee – Thank you for all your help, support and motivation. I would also wish to acknowledge Assoc. Prof. Dr. Tan Wen Siang, Assoc. Prof. Dr. Asmah Yahaya, and Dr. Firoozeh for all their guidance and advices.

Last but not least, I would like to express my deepest appreciation to my greatest supporters – my family. To my two pillars of success; my mother and father, Nor Inchun and Masarudin, my brothers Andi and Afzal, my sisters Aiysha and Atiqah, and my dearest fiancé Nur Afifah – thank you so much for your endless support, motivation, encouragements and for being very understanding towards me and my work. Thank you to my uncles and aunties, especially Pak Tam, Mak Tam, my grandfather Mohd Salleh, my grandmother Jemiah Mehat, Uncle Ijap, Auntie Noriah, and all my cousins for their prayers.

I wish to extend my appreciation to everyone, friends and family, although not individually acknowledged here for their direct or indirect effort and contribution to this study. Thank you everyone, for your support and love.

I certify that an Examination Committee met on 10th October 2008 to conduct the final examination of Mas Jaffri Masarudin on his Master of Science entitled "Synthesis and Characterization of Novel Plasmid-Layered Double Hydroxides Nanobiohybrids for Gene Delivery" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The committee recommends that the student be awarded the Master of Science.


Members of the Examination Committee were as follows:

Tan Wen Siang, PhD
Associate Professor
Faculty of Biotechnology and Biomolecular Sciences
Universiti Putra Malaysia
(Chairman)

Asmah Hj. Yahaya, PhD
Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Mohd. Puad Abdullah, PhD
Lecturer
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Shahidan Radiman, PhD
Professor
Faculty of Science and Technology
Universiti Kebangsaan Malaysia
(External Examiner)



HASANAH MOHD. GHAZALI, PhD
Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 27 November 2008

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

Khatijah Mohd. Yusoff, PhD

Professor
Department of Microbiology
Faculty of Biotechnology and Biomolecular Sciences
Universiti Putra Malaysia
(Chairman)

Mohd Zobir Hussein, PhD

Professor
Department of Chemistry
Faculty of Science
Universiti Putra Malaysia
(Member)

Raha Abdul Rahim, PhD

Professor
Department of Cell and Molecular Biology
Faculty of Biotechnology and Biomolecular Sciences
Universiti Putra Malaysia
(Member)



HASANAH MOHD/ GHAZALI, PhD
Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 18 December 2008

DECLARATION

I declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously and is not concurrently submitted for any other degree at UPM or at any other institution.

A handwritten signature in black ink, appearing to read 'Mas Jaffri', is written over a horizontal line.

MAS JAFFRI MASARUDIN

Date: 28 October 2008

TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	iv
ACKNOWLEDGEMENTS	vii
DECLARATION	xi
LIST OF TABLES	xv
LIST OF FIGURES	xvi
LIST OF ABBREVIATIONS	xviii
 CHAPTER	
 1 INTRODUCTION	 1
 2 LITERATURE REVIEW	
2.1 Nanotechnology for biological sciences	4
2.2 Layered Double Hydroxides	
2.2.1 Structural composition and properties	7
2.2.2 Anionic exchange properties of Layered Double Hydroxides	10
2.2.3 Synthesis route of LDH	11
2.3 Applications and uses of LDH	12
2.3.1 LDH for pharmaceutical and medical applications	13
2.3.2 LDH for environmental applications	17
2.3.3 LDH for industrial applications	19
2.4 DNA-LDH Nanobiohybrids	20
2.5 The guest anion, plasmid DNA	23
2.5.1 Plasmid pEGFP-N2	25
2.6 Cellular transfection for gene delivery into cells	27
2.7 Cytotoxicity Tests – The MTT Assay	28
 3 MATERIALS AND METHODS	
3.1 Materials	31
3.2 Preparation of guest anion, pEGFP-N2	
3.2.1 Cloning of pEGFP-N2 into bacteria <i>Escherichia coli</i>	31
3.2.2 Plasmid Extraction	32
3.2.3 Purification of plasmid DNA with PEG/MgCl ₂	34
3.2.4 Determination of DNA concentration and purity	35
3.3 Restriction Enzyme Analysis	36
3.4 Agarose gel electrophoresis of pEGFP-N2	36
3.5 Synthesis of pristine Mg/Al-LDH host	37
3.6 Synthesis of Nanobiohybrids	40
3.6.1 Self-Assembly method	40
3.6.2 Ion-Exchange method	40



3.7	Analysis of reaction supernatant	41
3.8	Recovery of pEGFP-N2 from NB	41
3.9	Powder X-Ray Diffraction	43
3.10	Fourier-Transform Infrared Spectroscopy	43
3.11	Inductively Coupled Plasma-Atomic Emission Spectroscopy	44
3.12	Carbon, Hydrogen, Nitrogen and Sulphur Analysis	44
3.13	Scanning Electron Microscopy	45
3.14	Transmission Electron Microscopy	45
3.15	Cell culture	
3.15.1	Propagation of cells	45
3.15.2	MTT Assay	46
3.15.3	Cellular Transfection of Vero3 Cell Line	50
3.16	Treatment of NB with DNase I enzyme	51
3.17	Treatment of NB with <i>KpnI</i> / <i>XhoI</i> restriction enzymes	51
4	RESULTS AND DISCUSSION	
4.1	Preparation of guest anion, plasmid pEGFP-N2	53
4.2	Extraction and purification of guest anion, pEGFP-N2	54
4.3	Synthesis of pristine MgAl-NO ₃ ⁻ LDH nanohosts	56
4.3.1	Selection of LDH hosts for anion exchange reactions	59
4.4	Anion exchange reactions of pEGFP-N2 with MgAl-NO ₃ ⁻ LDH	60
4.4.1	Powder x-ray diffraction of synthesized NB	61
4.4.2	Analysis of supernatant from anion exchange reactions	66
4.4.3	Recovery of pEGFP-N2 from NB	69
4.5	Fourier-Transform Infrared study	73
4.6	Elemental analysis of synthesized samples	78
4.6.1	Inductively-Coupled Plasma Atomic Emission Spectroscopy Analysis	78
4.6.2	Carbon, Hydrogen, Nitrogen and Sulphur Analysis	79
4.7	Size and morphological studies of samples	
4.7.1	Scanning Electron Microscopy of synthesized NB and LDH samples	80
4.7.2	Transmission Electron Microscopy of synthesized NB and LDH samples	84
4.8	Toxicity evaluation of MgAl-NO ₃ ⁻ using MTT assay	87
4.8.1	Cytotoxicity of MgAl-NO ₃ ⁻ LDH on Cell Lines	88
4.8.2	Influence of MgAl-NO ₃ ⁻ LDH R _i on cell toxicity	89
4.9	Cellular transfection of Vero3 Cell Line with NB-R ₂	95
4.10	Treatment of NB with restriction enzymes and endonucleases	101
4.10.1	Treatment with DNase I enzyme	101
4.10.2	Treatment with <i>XhoI</i> and <i>KpnI</i> restriction enzymes	103
5	CONCLUSIONS	106

REFERENCES	108
BIODATA OF STUDENT	
LIST OF SEMINARS AND CONFERENCES	
LIST OF ACHIEVEMENTS	
LIST OF PUBLICATIONS	

LIST OF TABLES



Table	Page
2.1 Drug delivery technologies at nanoscale level	14
3.1 Chemical composition used for MgAl-NO ₃ ⁻ hosts synthesis	38
4.1 List of F-TIR bands for synthesized LDH and NB samples	77
4.2 Chemical compositions for MgAl-NO ₃ ⁻ hosts and NB-R ₂ synthesized	81
4.3 Carbon, hydrogen, nitrogen and sulphur content in LDH-R ₂ and NB-R ₂ samples	81

LIST OF FIGURES



Figure		Page
2.1	The hexagonal plane structure of the layers contained in (a) CaAl-LDH, (b) LiAl-LDH and (c) MgAl-LDH	9
2.2	The anion exchange mechanism of LDH	10
2.3	The intercalation of various biomaterials into (a) MgAl-NO ₃ ⁻ LDH hosts through ion exchange reactions; from (b) CMP, (c) AMP, (d) GMP, and even (e) DNA	21
2.4	The delivery of intercalated RNA into the cell	22
2.5	The many forms of plasmid DNA	24
2.6	The generic map of the pEGFP-N2 plasmid DNA	26
3.1	The (a) general assembly for pristine LDHs synthesis; and (b) assembly of burette, pH meter and N ₂ gas source	39
3.2	Diagram showing the synthesized LDH/NB slurry after centrifugation, comprised of the reaction supernatant (A) and product slurry (B) area	42
3.3	Diagram showing the (i) 96-well plate used for MTT assay and (ii) concentrations of the inorganic host used for treatment	48
3.4	Diagram showing the 6-well plate used for transfection of samples	49
4.1	Gel electrophoresis of the plasmid extracted from the recombinant <i>E. coli</i>	55
4.2	PX-RD spectra of the LDH host synthesized at different Mg/Al ratios (R _i) via co-precipitation with NaOH at pH 10.0	58
4.3	PX-RD patterns of synthesized NB-R ₂	62
4.4	PX-RD patterns of synthesized NB-R ₄	63
4.5	The different possible orientations of nitrate (NO ₃ ⁻) anions inside the LDH interlayer	65
4.6	Gel electrophoresis of (a) reaction supernatant recovered from anion exchange reactions, and (b) repeated washings of the	

	synthesized NB samples	67
4.7	Gel electrophoresis of pEGFP-N2 plasmid DNA recovered from the LDH host	70
4.8	Supercoiling of plasmid DNA	72
4.9	F-TIR spectra of DNA, NB-R ₂ (R ₂ + 0.35 mg/ml pEGFP-N2), and LDH R ₂ (MgAl-NO ₃ ⁻ R ₂)	75
4.10	F-TIR spectra of DNA, NB-R ₄ (R ₄ + 0.50 mg/ml pEGFP-N2), and LDH R ₄ (MgAl-NO ₃ ⁻ R ₄)	76
4.11	SEM micrographs showing the surface morphologies of (a) LDH R ₂ and (b) NB-R ₂	82
4.12	SEM micrographs showing surface morphologies of (a) LDH R ₄ and (b) NB-R ₄	83
4.13	TEM micrographs showing size distributions for (a) LDH R ₂ and (b) NB-R ₂	85
4.14	TEM micrographs showing size distributions for (a) LDH R ₂ and (b) NB-R ₂	86
4.15	MTT assay showing cytotoxicity of LDH hosts (R ₁ -R ₅) towards Vero3 cells	90
4.16	MTT assay showing cytotoxicity of LDH hosts (R ₁ -R ₅) towards Chang Liver cells	91
4.17	MTT assay showing the cytotoxicity of metal salt solutions (MgAl-NO ₃ ⁻) towards Vero3 cells	93
4.18	Cellular transfection of Vero3 cells with (a) pEGFP-N2, (b) LDH-R ₂ , and (c) NB-R ₂	96
4.19	Cellular transfection of Vero3 cells with (b) LDH-R2 and (c) Lipo-DNA (Lipofectamine TM 2000 + pEGFP-N2)	100
4.20	Gel electrophoresis of pEGFP-N2 plasmid DNA recovered from NB-R ₂ treated with DNase I	102
4.21	Gel electrophoresis of pEGFP-N2 plasmid DNA recovered from NB-R ₂ treated with <i>Xho</i> I/ <i>Kpn</i> I restriction enzymes	104

LIST OF ABBREVIATIONS

Å	Angstrom
ADA	Adenosine deaminase
ATP	Adenosine triphosphate
NB	Nanobiohybrid(s)
CHO	Chinese Hamster Ovarian
C	Carbon
CHNS	Carbon, Hydrogen, Nitrogen, Sulphur
CNT	Carbon nanotubes
CO ₂	Carbon dioxide
°C	Degree Celsius
CMP	Cytosine Mono Phosphate
DMEM	Dulbecco's Modified Eagle's Medium
DMSO	dimethylsulfoxide
DNA	deoxyribonucleic acid
EDTA	ethylene diamine tetraacetic acid
FCS	Foetal Calf Serum
F-TIR	Fourier-Transform Infrared
GFP	Green Fluorescent Protein
µg	microgram
mg	milligram
g	gram
h	hour
IC ₅₀	Inhibition Concentration at 50% Viability

ICP-AES	Inductive Couple Plasma – Atomic Emission Spectroscopy
LDH	Layered Double Hydroxide
ml	millilitre
M	molar
M^{2+}/M^{II}	Divalent metal cation
M^{3+}/M^{III}	Trivalent metal cation
mRNA	Messenger RNA
MTT	methyl thiazol tetrazolium bromide
MTX	Methotrexate
N	Nitrogen
nm	nanometer
PBS	Phosphate Buffered Saline
PEG	Poly Ethylene Glycol
PX-RD	Powder X-Ray Diffraction
RNA	Ribonucleic Acid
RNAi	RNA interference
SEM	Scanning Electron Microscope
siRNA	Small interfering RNA
TAE	Tris-Acetate-EDTA
TE	Tris-EDTA
TGA-DTG	Thermal Gravimetry Analysis – Derivatives Thermal Gravimetry
Θ	X-Ray diffraction angle

CHAPTER 1

INTRODUCTION

Many recent understandings and significant conceptual findings of modern day research have evolved to include a mainly interdisciplinary approach; slowly diminishing the fine line separating the many fields of physical, chemical and biological sciences. These revolutions in how researchers perceive, conceive, and conduct their work are now inclined towards the early conceptual genesis of nanobiotechnology - the fusion between biotechnology; the field of biological sciences directed at the manipulation of biological systems, with nanotechnology; the science of materials one-billionth of a metre.

The emphasis over nanobiotechnological research throughout the last few years, has been tremendously directed on the fabrication of various nanomaterials (Jain, 2005) such as inorganic and organic nanoparticles, fullerenes, dendrimers and layered double hydroxides for delivery of therapeutics; well-designed to suit and overcome the many biological barriers that presently hinders present drug delivery systems. Usually referred to as non-viral vectors, their usage has received considerable interest over the past few years. Using these materials is advantageous due to its ability to be designed and synthesized from the ground up for tailored specificity;

henceforth leading towards the discovery of new drug and delivery systems. Because of its very small size ($\sim 10^{-9}$ m) uptake into cells would be vastly improved by either simple diffusion or endocytosis, or even by enzymatic breakdowns in the acidic environments of the lysosome (Kwak *et al.*, 2004).

The efficient delivery for new-age therapeutics such small-interfering RNA (siRNA), DNA and RNA aptamers as well as plasmid DNA for gene therapy faces many hindering biological barriers. Direct administration of such biomaterials would usually result in their premature denaturation and degradation within cellular environments (Xu *et al.*, 2006). This is because both the intracellular as well as extracellular spaces of cells are flooded with the actions of endonucleases (enzymes) that cleave and degrade foreign invasive DNAs entering the cells. Due to these obstacles, therapeutic DNA relies solely upon the development of various delivery vector systems.

Layered double hydroxides (LDH) are anionic clays that have the ability to encapsulate, or 'contain' various negatively charged moieties within its interlayer spacing. The process, known as intercalation, involves the insertion of a guest material within a layered material to retain its compositional structure (Cavani *et al.*, 1991). This inorganic, nano-sized material can therefore be used to accommodate many bioactive materials, such as oligopeptides and amino acids (Aisawa *et al.*, 2006), DNAs (Oh *et al.*, 2006), pesticides (Li *et al.*, 2004b), herbicides (Legrouri *et al.*, 2005), as well as hydrophobic molecules (Wang *et al.*, 2005) by electrostatic interactions within its intergallery spacing. Studies utilizing the nanomaterial have shown to

increase the delivery efficiencies of many biomolecules; which has included many drugs (Li *et al.*, 2004a; Oh *et al.*, 2006a), antibiotics (Tammaro *et al.*, 2007; Trikeriotis and Ghanotaxis, 2007), and even therapeutic DNA and genes (Kwak *et al.*, 2002; Tyner *et al.*, 2004). Furthermore, encapsulation within an LDH host offers protection of the biomolecules from degradation by nucleases (Oh *et al.*, 2006a) and enzymes thus their delivery can also be dose-controlled.

This study aims to evaluate whether LDH can be used as an alternative gene delivery vector; by intercalating a type of circular DNA called plasmid DNA which contains a green fluorescent protein (GFP) gene into synthesized MgAl-NO_3^- LDH hosts. By using these inorganic hosts to encapsulate and protect the plasmid DNA within cellular environments, it is hypothesized that their uptake and expression in transfected cells will be enhanced and significantly increased compared to naked DNA delivery methods and conventional gene delivery vectors present in the market. Therefore the objectives set for this study are as follows;

1. to synthesize MgAl-NO_3^- layered double hydroxides via the coprecipitation method at different molar ratios (R_i),
2. to intercalate plasmid DNA into the synthesized MgAl-NO_3^- , and characterize the newly formed plasmid-LDH nanobiohybrids,
3. to evaluate any cytotoxicity the host, MgAl-NO_3^- has towards cells, and
4. to perform cellular transfection of cells using the synthesized nanobiohybrids for GFP gene expression.

CHAPTER 2

LITERATURE REVIEW

2.1 Nanotechnology for biological sciences

The term nanotechnology often conforms to many definitions in various modern sciences, but it has since been commonly regarded as the science of one-billionth of a metre. It involves the design, construction and use of functional nano-meter sized materials fabricated for a dimensional array of uses (Park *et al.*, 2007b; Alexis *et al.*, 2008). Although their sizes usually vary from 1-100 nm, by definition these small sizes must prove to play a vital part for its functionality.

The advent of nanotechnology has opened up many opportunities that can be utilized in a wide area of sciences such as engineering, material sciences, environmental sciences, healthcare and even the life sciences. However, research in the fields of nanomedicine and nanobiotechnology have been regarded to receive the most significant impact from this 'small-scaled' technology; with increasing interests into fabricating novel nanomaterials that have the ability to overcome many biological barriers currently present in biological systems (Alonso, 2004; Freitas Jr., 2005).

Such biological materials that are being developed are known as nanoparticles; spherical structures in the nanometer range sizes, extensively studied as a vector for improved delivery of functional biomaterials. Nanoparticles are highly flexible nano-structures due to their uniquely small sizes, which have been used to increase the delivery efficiency of various biomaterials. These materials are easily synthesized usually using polymeric biocompatible materials such as chitosan and dextran as the encapsulation vector; the particles are readily degraded within the cell upon entry to release the encapsulated biomaterials. Chen *et al.* (2007a) and Zhang *et al.* (2007) discovered in their studies that the encapsulation of an immunosuppressant drug, rapamycin and the diabetic drug, insulin within cholesterol and PEG-modified chitosan nanoparticles increased their permeability and delivery uptake into cells; showing a slow-sustained release of the proteins *in vivo*. While such properties were common in numerous other studies (Jiang *et al.*, 2005; Wang *et al.*, 2006; Krauland & Alonso, 2007; Puri *et al.*, 2007), research has now progressed onto the development of new-targeted nanoparticles for specific delivery in the cell and human body (Jain, 2005; Rieux *et al.*, 2006; Breunig *et al.*, 2007).

Nanoparticles have been studied in the treatment of many types of cancer (Alexis *et al.*, 2008) involving construction of novel nucleic acid-nanoparticle conjugates, which can target specific cancer genes for mRNA silencing (Woodle & Lu, 2005) for different cancers including human liver cancer (Park *et al.*, 2007a) and breast cancer (Nguyen *et al.*, 2007).